



# Product Data Sheet

## Transobox Unikote 2.45

### Product description.

A one coat system combining priming and finishing qualities for easy and refurbishment of containers. Corrosion protection is provided by non-toxic anti-corrosive pigments dispersed in water repelling chlorinated rubber resins.

### Physical properties.

Colour/Texture	Wide Colour Range/Semi-gloss
Volume Solids	48%
Specific gravity	1.35~1.42 gr/ml ( depend on colour ).
VOC	458 gr/liter
Flashpoint	>24°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m <sup>2</sup> /l)
Range	50 – 100	105 – 208	9.6 – 4.8
Recommended	70	145	6.8

### Application data.

Guiding data Airless spray Pressure at nozzle: 120 – 150 bar. Nozzle size: 0.38 - 0.53 mm.  
Spray angle: 40 - 80 degrees.

Guiding data Airspray Volume of thinner: 0 – 3%.  
Pressure. 3 – 4 bar. Nozzle size: 1.2 - 2.0 mm.  
Volume of thinner: 0 – 5%.

Brush/Roller Suitable. Multicoats may be required to achieve the required dry film thickness. Volume of thinner: not more than 10%.

Thinner/Cleaner Transocean Special Thinner 6.01

Conditions Humidity: below 90% RH  
Temperature of the paint before application: min: 5°C, max: 30°C.  
Substrate temperature: min: 1°C, max: 35°C.  
The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

### Drying and recoating times.

Substrate temperature	Touch dry	Hard dry	Dry to recoat	
			Minimum	Maximum (1)
10 °C	2 hours	24 hours	24 hours	Indefinite
23 °C	1 hour	12 hours	4 hours	Indefinite
30 °C	30 minutes	8 hours	8 hours	Indefinite

- (1) The surface should be dry and free from contaminants prior to overcoating. After prolonged exposure times it may be necessary to roughen the surface to ensure intercoat adhesion.  
When in doubt, consult your nearest Transocean office.

## Surface preparation.

Steel	Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Remove weld spatter and smooth weld seams and sharp edges as applicable. Abrasive blasting: min. Sa 2,5 – ISO 8501:1. Apply Transobox Unikote 2.45 immediately after the steel has been blasted and the quality of preparation has been approved.
Repair	Corroded areas should be power tool cleaned to ISO-St 3 or blast cleaned to ISO-Sa 2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

## Recommended paint system.

A typical system for container exteriors is shown below.

Transobox Unikote 2.45	2 x 70 µ dft.
------------------------	---------------

## Worldwide availability

The product is part of the common Transocean product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and/or national regulations. In such cases an alternative datasheet will be issued.

## Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately.

Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

## Disclaimer

*The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.*

*Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.*

*We reserve the right to change the product without notice.*

Date of issue: November, 09.



## KOSSAN PAINT (M) SDN.BHD

1, Jalan Koporat 1/KU9, Taman Perindustrian Meru,  
Kapar, 42200 Klang Selangor D.E Malaysia.

Tel. 33922799 Fax.33923799 e-mail : lskheong@kop.com.my  
web-site : www.kossanpaint.com